

RIVERBANK ACOUSTICAL LABORATORIES

1512 S. BATAVIA AVENUE
EVEA, ILLINOIS 60134

OF
IIT RESEARCH INSTITUTE

630/232-0104
FOUNDED 1918 BY
WALLACE CLEMENT SABINE

REPORT

FOR: Auralex Acoustics

Sound Absorption Test
RAL™-A02-23

ON: Auralex Studiofoam 1124ST

Page 1 of 4

CONDUCTED: 12 February 2002

TEST METHOD

The test method conformed explicitly with the requirements of the ASTM Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method: ASTM C423-90a and E795-00. Riverbank Acoustical Laboratories has been accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) for this test procedure. A description of the measuring technique is available separately.

DESCRIPTION OF THE SPECIMEN

The test specimen was designated by the manufacturer as Auralex Studiofoam 1124ST. The overall dimensions of the specimen as measured were 2.44 m (96 in.) wide by 2.74 m (108 in.) long and 51 mm (2 in.) thick. The specimen consisted of seventy-two (72) pieces. Each piece was 305 mm (12 in.) wide by 305 mm (12 in.) long and 51 mm (2 in.) thick. The specimen was tested in the laboratory's 292 m³ (10,311 ft³) test chamber.

The manufacturer's description of the specimen was as follows: Studiofoam 1124ST, 2" thick sawtooth-cut foam. Each unit is 12" x 12" x 2". Open cell foam, 0.5" thick at the valley, 2" thick at the peak of a sawtooth. The foam is nominal 2 pounds per cubic foot density. A visual inspection verified the manufacturer's description of the specimen.

The weight of the entire specimen as measured was 5.2 kg (11.5 lbs), an average of 1 kg/m² (0.2 lbs/ft²). The area used in the calculations was 6.7 m² (72 ft²). The room temperature at the time of the test was 21°C (69°F) and 61% relative humidity.

MOUNTING A

The test specimen was laid directly against the test surface.

THE RESULTS REPORTED ABOVE APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR MEASUREMENT. NO RESPONSIBILITY IS ASSUMED FOR PERFORMANCE OF ANY OTHER SPECIMEN.



ACCREDITED BY DEPARTMENT OF COMMERCE, NATIONAL VOLUNTARY LABORATORY
ACCREDITATION PROGRAM FOR SELECTED TEST METHODS FOR ACOUSTICS.
THE LABORATORY'S ACCREDITATION OR ANY OF ITS TEST REPORTS IN NO WAY CONSTITUTES
OR IMPLIES PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY NIST.

RIVERBANK ACOUSTICAL LABORATORIES

1512 S. BATAVIA AVENUE
EVEA, ILLINOIS 60134

OF
IIT RESEARCH INSTITUTE

630/232-0104
FOUNDED 1918 BY
WALLACE CLEMENT SABINE

REPORT

Auralex Acoustics

RAL™-A02-23

12 February 2002

Page 2 of 4

TEST RESULTS

1/3 Octave Center Frequency (Hz)	Absorption Coefficient	Total Absorption In Sabins	% Of Uncertainty With 95% Confidence Limit With Specimen
100	0.15	10.76	3.03
** 125	0.16	11.64	2.32
160	0.18	12.98	2.29
200	0.23	16.48	1.54
** 250	0.29	20.86	1.29
315	0.41	29.67	1.00
400	0.49	35.61	1.05
** 500	0.57	41.26	0.94
630	0.66	47.78	0.80
800	0.72	51.57	0.67
** 1000	0.75	53.98	0.64
1250	0.78	56.08	0.65
1600	0.84	60.44	0.47
** 2000	0.90	64.98	0.55
2500	0.91	65.55	0.45
3150	0.94	67.95	0.43
** 4000	1.00	72.27	0.42
5000	1.08	77.68	0.40

NRC = 0.65

THE RESULTS REPORTED ABOVE APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR MEASUREMENT. NO RESPONSIBILITY IS ASSUMED FOR PERFORMANCE OF ANY OTHER SPECIMEN.



ACCREDITED BY DEPARTMENT OF COMMERCE, NATIONAL VOLUNTARY LABORATORY
ACCREDITATION PROGRAM FOR SELECTED TEST METHODS FOR ACOUSTICS.
THE LABORATORY'S ACCREDITATION OR ANY OF ITS TEST REPORTS IN NO WAY CONSTITUTES
OR IMPLIES PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY NIST.

RIVERBANK ACOUSTICAL LABORATORIES

1512 S. BATAVIA AVENUE
EENEVA, ILLINOIS 60134

OF
IIT RESEARCH INSTITUTE

630/232-0104
FOUNDED 1918 BY
WALLACE CLEMENT SABINE

REPORT

Auralex Acoustics

RAL™-A02-23

12 February 2002

Page 3 of 4

TEST RESULTS (Continued)


The percentage of uncertainty for the required 95% confidence limits indicated above must fall within the prescribed limits designated in par. 13.2 of ASTM C423-90a. It states that for the absorption of the reverberation room containing the specimen the testing laboratory shall obtain data with less than 4% uncertainty at 125 (hertz) and 2% uncertainty at 250, 500, 1000, 2000, and 4000 (hertz). The method of calculation is described in ASTM STP 15D and outlined in section 13 of the standard.

The noise reduction coefficient (NRC) is the average of the coefficients at 250, 500, 1000, and 2000 Hz, expressed to the nearest integral multiple of 0.05.

Tested by


Dean Victor
Senior Experimentalist

Approved by


David L. Moyer
Laboratory Manager

THE RESULTS REPORTED ABOVE APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR MEASUREMENT. NO RESPONSIBILITY IS ASSUMED FOR PERFORMANCE OF ANY OTHER SPECIMEN.



ACCREDITED BY DEPARTMENT OF COMMERCE, NATIONAL VOLUNTARY LABORATORY
ACCREDITATION PROGRAM FOR SELECTED TEST METHODS FOR ACOUSTICS.
THE LABORATORY'S ACCREDITATION OR ANY OF ITS TEST REPORTS IN NO WAY CONSTITUTES
OR IMPLIES PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY NIST.

RIVERBANK ACOUSTICAL LABORATORIES

1512 S. BATAVIA AVENUE
EENEVA, ILLINOIS 60134

OF
IIT RESEARCH INSTITUTE

630/232-0104


FOUNDED 1918 BY
WALLACE CLEMENT SABINE

REPORT

SOUND ABSORPTION REPORT

RAL - A02-23

PAGE 4 OF 4



NRC = 0.65

THE RESULTS REPORTED ABOVE APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR MEASUREMENT. NO RESPONSIBILITY IS ASSUMED FOR PERFORMANCE OF ANY OTHER SPECIMEN.



ACCREDITED BY DEPARTMENT OF COMMERCE, NATIONAL VOLUNTARY LABORATORY
ACCREDITATION PROGRAM FOR SELECTED TEST METHODS FOR ACOUSTICS.
THE LABORATORY'S ACCREDITATION OR ANY OF ITS TEST REPORTS IN NO WAY CONSTITUTES
OR IMPLIES PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY NIST.